



Main Office
53-57 Van Dyke Street
Wallington, NJ 07057
(201) 935-2777
(800) 524-1592
(201) 935-5961 Fax
www.triangleink.com

STA-TRUE
1702
LOW BLEED ALPINE WHITE

GENERAL DESCRIPTION:

Sta-True 1702 plastisol ink is formulated for printing on polyester and 50/50 polyester/cotton blends, where normal plastisol films would be discolored due to the fabric dyes migration into the screen printed film. Alpine White is formulated to give a soft touch to the fully cured film, it can be printed direct onto the garment as well as transferred onto the garment. It is highly recommended that test prints always be performed prior to production runs..

STOCK:

Polyester and 50/50 polyester/cotton blends.

STENCILS:

All types of solvent resistant emulsions are suitable.

SCREEN MESH:

110T monofilament is the popular choice; printers may also employ the use of mesh sizes 60T to 110T monofilament or equivalent.

CURING:

315° F TO 330° F depending on ink deposit, color and dryer efficiency.

WASH-UP:

Tri-sol 25 or equivalent (Mineral Spirits).

MIXING PROCEDURES:

Stir well before using. For best results, do not add any reducers or additives to this ink.

CAUTION:

It is necessary to pre-test all fabrics prior to production, due to the various dye application methods. Ink films must be cured properly to give good wash resistance and in some cases to prevent 'post-bleed' due to dye solubility. There is a tendency to under cure ink films to prevent dye migration due to heat, but this will only result in other problems. Some fabrics may need to be pre-heated to "set" the dyes - this is not altogether desirable, but will produce a more thorough cure due to moisture removal as well.

STORAGE PROCEDURE:

Store at room temperature. Keep away from heat.

WARNING: FOR INDUSTRIAL USE ONLY KEEP AWAY FROM CHILDREN

NOTE: Please note that all colors are made without the use of lead or heavy metal pigments. This product is CPSIA compliant. The information on this data sheet is based on laboratory tests and production experience. Directions and procedures for use of Triangle-Ink products must be considered as recommendations only. The printer is solely responsible for determining suitability of any Triangle product for a specific application. We recommend that all products be pre-tested prior to production. No warranties are implied or expressed.

53-57 Van Dyke Street, Wallington, New Jersey 07057 • (201) 935-2777 • (800) 524-1592 • FAX (201) 935-5961